

## Green Synthesis of TiO<sub>2</sub> Nanoparticles: A Cost Effective Approach

S.S.N.Fernando<sup>1</sup>, M.M.K.Peiris<sup>1</sup>, T.D.C.P.Gunasekara<sup>1</sup>, N.D.H.Arachchi<sup>1</sup>, P.M.Jayaweera<sup>2</sup>

Titanium dioxide (TiO<sub>2</sub>) nanoparticles (NPs) are very useful for many purposes due to their unique physical and chemical properties. Biological synthesis of TiO<sub>2</sub> NPs is poorly understood compared to chemical and physical synthesis methods. The present investigation was undertaken to synthesize TiO<sub>2</sub> NPs using Baker's Yeast by a low-cost and sustainable process. For yeast mediated TiO<sub>2</sub> NP synthesis, yeast was cultured in sterile filtered 5% (w/v) glucose solution and incubated for 24 h. After that, TiCl<sub>3</sub> was added slowly until a clear purple solution observed. Then the solution was allowed to stand at room temperature under dark conditions for three days. The solution was centrifuged and the precipitate was washed several times with sterile distilled water, dried at room temperature and oven-dried at heating periods of 250, 350, 450, 550, 650 and 750 °C for 2 h. Characterization of synthesized TiO<sub>2</sub> NPs was performed using X-ray diffraction (XRD), Transmission Electron Microscopy (TEM) and Scanning Electron Microscopy (SEM). Spherical TiO<sub>2</sub> NPs were observed with a large amount of thin TiO<sub>2</sub> lamellas. Lamellas were consisted of a large number of small TiO<sub>2</sub> NPs. XRD pattern of the NPs obtained by using yeast template was assigned to be pure anatase TiO<sub>2</sub> according to characteristic peak positions at 25.303 (1,0,1), 37.78 (1,0,3), 48.03 (2,0,0), 54.45 (1,0,5), 62.80 (2,1,3), 70.34 (2,2,0), 74.91(1,0,7) and 82.81 (3,0,3) degrees. The most predominant orientation was the (1,0,1) plane as the highest intensity was observed at 25.303. The particle size distribution was 3.6 – 12.0 nm with a mean particle size of 6.7 ± 2.2 nm as shown in TEM imaging. In this study, TiO<sub>2</sub> NPs were synthesized with TiCl<sub>3</sub> as the precursor salt, in an eco-friendly manner. The increased temperature induced crystallinity. Anatase phase TiO<sub>2</sub> NPs get converted into rutile phase within 600-700 °C range. The biosynthesized anatase TiO<sub>2</sub> NPs were thermally stable. Yeast cells were used as a biotemplate that can facilitate Ti<sup>3+</sup> adsorption followed by nucleation. The NPs were smaller with a narrow size distribution. The results suggest that Yeast mediated TiO<sub>2</sub> NP synthesis is a renewable and eco-friendly alternative to chemical synthesis.

**Keywords:** TiO<sub>2</sub>, anatase, TEM, SEM, lamella

---

<sup>1</sup>Department of Microbiology, Faculty of Medical Sciences, University of Sri Jayewardenepura, Sri Lanka\*[fneluka@sjp.ac.lk](mailto:fneluka@sjp.ac.lk)

<sup>2</sup>Department of Chemistry, Faculty of Applied Sciences, University of Sri Jayewardenepura, Sri Lanka